



Typical Properties Sheet

11/8/2018

Product: **XL2000/EVA**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Natural	
Density (lbs / ft3)	2.0	ASTM D 3575-93
Compressive Strength – @25%	6.8	ASTM D 3575-93 Suffix D
Compression Set (%)	15.4	ASTM D 3575-93 Suffix B
Tensile Strength (psi)	53.9	ASTM D 3575-93 Suffix T
Tear Resistance (lbs/inch)	12.9	ASTM D 3575-93 Suffix G
Water Absorption (lbs / ft2)	<1	ASTM D 3575-93 Suffix L
Working Temperature Range	-76 to 194 deg F	
Thermal Conductivity (btu/hr/inch ft/degF)	0.26	ASTM C177
Elongation (% to break)	345	ASTM D 3575-93

Note: blended with EVA

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

www.amconfoam.com