



Technical Data Sheet

6/2/2006

Product: **7600**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Charcoal Grey	
Density (lbs / ft ³)	5.4 - 6.6	ASTM D-3574-01
Compression Deflection @ 25% (psi)	0.65 min	ASTM D-3574-01
Tensile Strength (psi)	12 min	ASTM D-3574-01
Elongation (%)	150 min	ASTM D-3574-01
Tear Strength (lbs / lin inch)	1.5 min	ASTM D-3574-01
Flame Resistance	pass	UL94 HF-1

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

WARNING: URETHANE FOAM IS FLAMMABLE!
Urethane Foam should not be exposed to open flame or other ignition sources.
Urethanes burn rapidly with great heat and release gases which are extremely hazardous.

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

www.amconfoam.com